

Nitto

HYDRANAUTICS
Nitto Group Company

Membrane Element

SWC6-4040

Performance:

Permeate Flow:
Salt Rejection:
Applied Pressure:

Low Pressure:
1,250 gpd (4.7 m³/d)
99.6% (99.4 % min)
600 psi (4.1 MPa)

High Flow:
2,500 gpd (9.5 m³/d)
99.7% (99.5% min)
800 psi (5.4 MPa)

Type

Configuration:
Membrane Polymer:
Membrane Active Area:

Spiral Wound
Composite Polyamide
85 ft² (7.9m²)

Application Data*


Maximum Applied Pressure: 1000 psig (6.9 MPa)
Maximum Chlorine Concentration: < 0.1 PPM
Maximum Operating Temperature: 113 °F (45 °C)
pH Range, Continuous (Cleaning): 2-11 (1-13)*
Maximum Feedwater Turbidity: 1.0 NTU
Maximum Feedwater SDI (15 mins): 5.0
Maximum Feed Flow: 16 GPM (3.6 m³/h)
Minimum Recovery for any Element: 10 %
Maximum Pressure Drop for Each Element: 10 psi

* The limitations shown here are for general use. For specific projects, operating at more conservative values may ensure the best performance and longest life of the membrane. See Hydranautics Technical Bulletins for more detail on operation limits, cleaning pH, and cleaning temperatures.

Test Conditions

The stated performance is initial (data taken after 30 minutes of operation), based on the following low pressure conditions:

32,000 ppm NaCl
600 psi (4.1 MPa) Applied Pressure
77 °F (25 °C) Operating Temperature
10% Permeate Recovery
6.5 - 7.0 pH Range



A, inches (mm)	B, inches (mm)	C, inches (mm)	Weight, lbs. (kg)
40.00 (1016)	3.95 (100.3)	0.75 (19.1)	8 (3.6)

Core tube extension = 1.05" (26.7 mm)

Notice: Permeate flow for individual elements may vary + or - 20 percent. All membrane elements are supplied with a brine seal, interconnector, and o-rings. Elements are enclosed in a sealed polyethylene bag containing less than 1.0% sodium meta-bisulfite solution, and then packaged in a cardboard box.

Hydranautics believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Hydranautics assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Hydranautics' products for the user's specific end uses.

10/18/13